

Appl. No. 10/530,096
Amdt. Dated August 30, 2006
Reply to Office Action of June 1, 2006

RECEIVED
CENTRAL FAX CENTER
AUG 30 2006

Amendment to the Claims

This listing will replace all prior versions, and listings, of the claims in the application:

Listing of Claims:

Claim 1 (Cancelled)

Claim 2 (Currently amended): A sealing material in combination with an according to Claim 1, for use in sealing automobile engine cam cover wherein the sealing material seals the automobile engine cam cover and comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components,
covers.

Claim 3 (Currently amended): A sealing material ~~for cam covers~~ according to Claim 2, where a liquid acrylic polymer having a number average molecular weight M_n of 500 or more and a molecular weight distribution (M_w/M_n) of 1.8 or less is used as component (A) of the composition.

Appl. No. 10/530,096
Amdt. Dated August 30, 2006
Reply to Office Action of June 1, 2006

Claim 4 (Currently amended): A sealing material ~~for cam covers~~ according to Claim 2, where the cured product of the composition has a Duro A hardness of 45 or less.

Claim 5 (Currently amended): A sealing material ~~for cam covers~~ according to Claim 2, in combination with a for use in resin-made cam cover covers.

Claim 6 (Previously presented): An automobile engine cam cover sealed by a sealing material for cam covers according to Claim 2.

Claim 7 (Currently amended): A sealing material in combination with an according to Claim 1, for use as a sealing material for automobile engine oil pan wherein the sealing material seals the automobile engine oil pan and comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components.
~~pan.~~

Claim 8 (Currently amended): A sealing material ~~for oil pans~~ according to Claim 7, wherein a liquid acrylic polymer having a number average molecular weight M_n of 500 or more and a molecular weight distribution (M_w/M_n) of 1.8 or less is used as component (A) of the composition.

Appl. No. 10/530,096
Amdt. Dated August 30, 2006
Reply to Office Action of June 1, 2006

Claim 9 (Currently amended): A sealing material ~~for oil pans according to Claim 7~~, wherein the cured product of the composition has a Duro A hardness of 45 or less (according to JIS K6253).

Claim 10 (Currently amended): Automobile engine oil ~~pan~~ ~~pans~~ sealed by a sealing material for oil ~~pans which comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components.~~ ~~pans according to Claim 7.~~

Claims 11-14 (Cancelled):

Claim 15 (Currently amended): A sealing material in combination with an ~~according to Claim 1, for use in~~ automobile wire harness wherein the sealing material seals the automobile wire harness and comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components. harnesses.

Claim 16 (Currently amended): A sealing material ~~for automobile wire harnesses~~ according to Claim 15, wherein a liquid acrylic polymer having a number average molecular weight M_n of 500 or more

Appl. No. 10/530,096
Amdt. Dated August 30, 2006
Reply to Office Action of June 1, 2006

and a molecular weight distribution (M_w/M_n) of 1.8 or less is used as component (A) of the composition.

Claim 17 (Currently amended): A sealing material for ~~automobile wire harnesses~~ according to Claim 15, wherein the cured product of the composition has a Duro A hardness of 50 or less (according to JIS K6253).

Claim 18 (Currently amended): A sealing material for ~~automobile wire harnesses~~ according to Claim 15, wherein not more than 100 parts by weight of a reinforcing agent or a filler is added to the composition on the basis of 100 parts by weight of sum total of components (A), (B) and (C).

Claim 19 (Original): Automobile wire harnesses sealed by a sealing material for wire harnesses according to Claim 15.

Claims 20-31 (Cancelled)

Claim 32 (Currently amended): A sealing material for ~~automobile wire harnesses~~ according to Claim 17, wherein not more than 100 parts by weight of a reinforcing agent or a filler is added to the composition on the basis of 100 parts by weight of sum total of components (A), (B) and (C).

Appl. No. 10/530,096
Amdt. Dated August 30, 2006
Reply to Office Action of June 1, 2006

Claim 33 (Cancelled)